

Product Description

Temple-Inland® (VPB) veneer plaster base is an interior gypsum board with a specially formulated face paper that is designed to be used as a base for the application of thin-coat plaster systems. The face paper of this product is violet in color to indicate its enhanced absorption qualities. These qualities provide maximum adhesion of veneer plasters.

Advantages

- Provides appearance and surface of conventional plaster systems at less cost than regular plastering
- Easily and quickly installed using nail or screw application
- May be installed over wood or metal framing
- Available in 1/2" thickness with a regular core as well as 1/2" and 5/8" thicknesses with a fire-resistant core
- Fire resistance classified by Underwriters Laboratories according to ASTM E119¹
- Available with a minimum of 93% certified recycled content on a dry weight basis in accordance with ISO 14021 standards²

Limitations

- Not for exterior use
- Avoid exposure to prolonged, excessive temperatures: 125°F (52°C)
- Avoid exposure to excessive or continuous moisture
- Should be stored, handled and installed to comply with industry standards GA151 & ASTM C844

Applicable Standards

- Meets or exceeds ASTM C1396
- Federal Specification SS-L-30D, Type VI, Grade X & Grade R
- Application Standards ASTM C844 & GA151
- Surface Burning Characteristics ASTM E-84 Flame Spread 15 Smoke Developed 0

Submittal Approvals

JOB NAME: _____

CONTRACTOR: _____ DATE: _____

Product Data

WIDTH	LENGTH	THICKNESS / PRODUCT WEIGHT
4' (1219mm)	8' to 12' (2438mm to 3658mm)	1/2" (12.7mm) Reg, 1.6 lbs/ft ² 5/8" (15.9mm) FRX, 2.3 lbs/ft ² 5/8" (15.9mm) Type TG-C, 2.4 lbs/ft ²

Special Order Information: Other widths, edges and lengths may be available on special order with established minimums and lead time. Some products may not be available in all markets. Please check with your local Temple-Inland sales representative.

1. This material complies to ASTM E119 and therefore may provide a fire rating of one or more hours, depending on the system in which it is applied. Because ASTM procedures require that fire tests be conducted on complete building assemblies/systems and not just on the gypsum board itself, the ability of any particular 5/8" Type X gypsum board product to pass a specific ASTM fire test may well depend on factors other than the fire resistance of the gypsum board being tested. These factors include the other components used to construct the building system being tested, the manner in which the system is constructed and the inherent variability of ASTM fire tests.
2. The recycled content levels of board produced at our Cumberland City, Tennessee, Fletcher, Oklahoma, and West Memphis, Arkansas, facilities are third-party verified by Scientific Certification Systems (SCS).

